

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
24 June 2004 (24.06.2004)

PCT

(10) International Publication Number  
WO 2004/052989 A1

(51) International Patent Classification<sup>7</sup>: C08L 53/02

(21) International Application Number:  
PCT/EP2003/050931

(22) International Filing Date: 3 December 2003 (03.12.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
02027269.6 6 December 2002 (06.12.2002) EP

(71) Applicant (for all designated States except US): KRATON  
POLYMERS RESEARCH B.V. [NL/NL]; Badhuisweg 3,  
NL-1031 CM Amsterdam (NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): JOLY, Gert  
[BE/BE]; Kraton Polymers Research S.A., Monnet  
Centre, Avenue Jean Monnet 1, B-B-1348 Ottignies-Lou-  
vain-La-Neuve (BE). MOERENHOUT, Jaak Lodewijk  
[BE/BE]; Kraton Polymers Research S.A., Monnet  
Centre, Avenue Jean Monnet 1, B-B-1348 Ottignies-Lou-  
vain-La-Neuve (BE).

(74) Agent: KORTEKAAS, Marcel; Kraton Polymers Re-  
search B.V., Intellectual Property Services, P.O. Box  
37666, NL-1030 BH Amsterdam (NL).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,  
AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR,  
CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD,  
GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR,  
KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN,  
MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU,  
SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA,  
UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (BW, GH,  
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE,  
SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA,  
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

- with international search report
- before the expiration of the time limit for amending the  
claims and to be republished in the event of receipt of  
amendments

For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

(54) Title: STYRENIC BLOCK COPOLYMER COMPOSITIONS TO BE USED FOR THE MANUFACTURE OF TRANSPAR-  
ENT, GEL FREE FILMS.

(57) **Abstract:** A composition to be used for the manufacture of transparent, gelfree films, comprising: a) at least 65 wt% of a  
styrenic block copolymer, having a molecular structure according to the formula S- (I/B) -S (1) or [S- (I/B) ] n X (2) , wherein each  
S independently is a polymer block of predominantly styrene and (I/B) is a substantially random polymer block of predominantly  
isoprene and butadiene, wherein n is an integer equal to or greater than 2, and wherein X is the residue of a coupling agent, wherein  
said styrenic block copolymer having a poly(styrene) content in the range of from 28 to 31 % by weight, having poly(styrene) blocks  
S of a true molecular weight in the range of from 10,000 to 15,000, having a true molecular weight of the complete block copolymer  
in the range of from 110,000 to 160,000 and wherein the diblock S-(I/B) optionally occurs in a content of at most 20 mol%, b) from  
5 to 25 wt% of a second thermoplastic resin, c) from 1 to 10 wt% of a plasticizing oil, the sum of the percentages of the components  
a, b and c being 100%, and all weight percentages being relative to the weight of the complete composition and extruded or cast or  
blown mono- or multi-layer films prepared from them.